



ID.Code

PE-5124
---------

Material: PET

Thickness: 0.95 mm

Weight: 500±20 gr/m<sup>2</sup>

Air Permeability: 25-30 Lit/dm<sup>2</sup>/min at 2mbar

Temp.Max.Peaks: 160 C

Temp.Recommended: 150 C

	Warp	Weft
<b>Tensile strength (kg.f)</b>	3250	1750
<b>Elongation at break (%)</b>	35	35

General resistance : \*

Acids		Alkalies		Organic Solvents	Micro Organisms
Weak	Strong	Weak	Strong		
E	G	F	P	E	E

\* E: Excellent G: Good F: Fair P: Poor