



ID.Code

PE636
-------

Material: PET

Thickness: 0.55 mm

Weight: 320 gr/m<sup>2</sup>

Air Permability: 25-30 Lit/dm<sup>2</sup>/m

Temp.Max.Peaks: 160 C

Temp.Recommended: 130 C

	Warp	Weft
Tensile strength (kg.f)	3150	2200
Elongation at break (%)	20	40

General resistance : \*

Acids		Alkalies		Organic Solvents	Micro Organisms
Weak	Strong	Weak	Strong		
F	P	G	G	E	E

\* E: Excellent G: Good F: Fair P: Poor