



ID.Code

PE-740

Material: PET

Thickness: 0.7 mm

Weight : 320±5 gr/m²

Air Permeability: 120±5 L/m²/m

Temp.Max.Peaks: 160 C

Temp.Recommended: 120 C

	Warp	Weft
Tensile strength (kg.f)	2500	1700
Elongation at break (%)	35	30

General resistance : *

Acids		Alkalies		Organic Solvents	Micro Organisms
Weak	Strong	Weak	Strong		
E	G	F	P	E	E

* E: Excellent G: Good F: Fair P: Poor