



ID.Code

PP-5124

Material:	PP
Thickness:	0.95 mm
Weight:	500±20 gr/m ²
Air Permeability:	25-30 Lit/dm ² /min at 2mbar
Temp.Max.Peaks:	120 C
Temp.Recommended:	90 C

	Warp	Weft
Tensile strength (kg.f)	3250	1750
Elongation at break (%)	35	35

General resistance : *

Acids		Alkalies		Organic Solvents	Micro Organisms
Weak	Strong	Weak	Strong		
E	E	E	E	E	E

* E: Excellent G: Good F: Fair P: Poor