



ID.Code

PP6022

Material:

PP(Polypropylene)

Thickness:

0.5 mm

Weight :

350±15 gr/m²

Air Permeability:

120±20 L/dm²/min

Temp.Max.Peaks:

110 C

Temp.Recommended:

90 C

Surface treatment :

One side calender

	Warp	Weft
Tensile strength (kg.f)	3250	2350
Elongation at break (%)	15	20

General resistance : *

Acids		Alkalies		Organic Solvents	Micro Organisms
Weak	Strong	Weak	Strong		
E	E	E	E	E	E

* E: Excellent G: Good F: Fair P: Poor